

## ABSTRACT OF THE DISCLOSURE

One object of the present invention is to provide a paste that is easily coated, has a comparatively long aging time and is able to maintain the shape of the ribs following plastic deformation; in order to achieve the object, the present invention provides a paste comprising 50-95 % by weight of glass powder or glass-ceramic mixed powder, 0.1-15 % by weight of a resin, and 3-60 % by weight of a plurality of kinds of solvents, wherein each boiling point of the plurality of kinds of solvents differs by 30°C or more; and, the plurality of kinds of solvents contain one or more low boiling point solvents which are low boiling point solvents having a boiling point from 100°C to 180°C, and one or more high boiling point solvents which are high boiling point solvents having a boiling point from 190°C to 450°C.

2010-12-23 10:40:40